Chemical Resistance of ENSINGER Engineering Plastics

CHEMICAL AGENTS

| Trade Name | Raw Material Group | Acetamide 50% | Acetic Acid conc. | Acetic Acid 10% | Acetic Acid 5% | Acetone | Ammonia 10% | Benzene | Bitumen | Boric Acid 10% | Butylacetate | Butylene Glycol | Calcium Chloride 10% | Carbon Disulphide | Carbon Tetrachloride | Chlorobenzene | Chloroform | Citric Acid 10% | Clophen A 60 50% | Copper Sulphate | Cyclohexane | Cyclohexanol | Cyclohexanone | Decahydronaphthalene | Diesel Oil | Dimethylformamide | Dioctylphthalate | Dioxane | Edible Oil, Edible Fat | Ethanol 96% | Ether | Ethyl Acetate | Ethylene Chloride | Formaldehyde 30% | Formamide | Formic Acid 10% | Frigen, Freon | Fruit Juices | Fuel Oil | Gasoline | Glycerine | Glycol | Glysantin 40% | Heptane/Hexane | Hydrochloric Acid 36% | Hydrofluoric Acid 2% | Hydrogen Peroxide 30% | Hydrogen Peroxide 0.5% | Hydrogen Sulphide | Ink | Isooctane | Isopropanol | Lactic Acid 90% | Lactic Acid 10% | Linseed Oil | Methanol | Methyl Ethyl Ketone | Methylene Chloride | Milk | Motor Oil/Engine Oil | Nitric Acid 2% | Nitrobenzene | Oxalic Acid 10% | Ozone | Paraffin Oil | Perchlorethylene | Petroleum White Spirit | Phenol, Aqueous | Phosphoric Acid 10% | Potassium Hydroxide Solution 10% | Potassium Hydroxide Solution 50% | Potassium Dichromate 10% | Potassium Permanganate 1% | Propanol | Pyridene | P3-Solution, Aqueous | Salicylic Acid | Silicone Oil | Soap Solution | Soda Solution 10% | Sodium Bisulphite | Sodium Carbonate 10% | Sodium Chloride 10% | Sodium Hydroxide Solution 50% | Sodium Nitrate 10% | Sodium Thiosulphate | Styrene | Sulphuric Acid 98% | Sulphuric Acid 2% | Tar | Tartaric Acid | Tetrahydrofuran | Tetrahydronaphthalene | Tincture of Iodine (alc.) | Toluene | Triethanolamine | Trichloroethylene | Trilon B 10% | Urea Aqueos | Vaseline | Water, Cold | Water, Hot | Wax, Molten | Wine, Brandy | Xylene | Zinc Chloride 10% |
|---|---|---